



47a Lara Way
Campbellfield Victoria 3061
Ph 9357 9510 Fax 9357 9908

200IL INTELAC MS

Intelac is a high quality, single component, nitrocellulose modified lacquer. It has been specifically designed for industrial application on interior furniture and general woodwork. Intelac delivers a high build with silky smooth feel.

- **Product:** Intelac modified nitrocellulose lacquer.
- **Gloss** 10%, 30%, 60%, 100% gloss levels
- **Thinning:** Lacquer Thinners, Universal slow reducer.
(Intelac MS may be thinned up to 10% by vol.)

- **Drying Time** Tack free 20-30 minutes. Recoat 2-3 hours.
(Oven curing for 20 min @ 40° C may reduce recoating schedule to approximately 30 min. Allow timber to cool to approximately ambient temperatures before recoating.)

- **Interior Exposure** Very Good
- **Yellowing Characteristics** Typical of nitrocellulose based lacquer
- **Water Resistance** Suitable only for splash resistance, typical of nitrocellulose lacquers. Wet areas should be coated with two component chemically resistant coatings such as polyurethanes.

- **Exterior Exposure** Not suitable (Must be protected from direct sunlight, rain and water condensation)

- **Container Size** 4Lt, 20Lt
- **Sealer** May be used as a self sealing system however for open grain timber it is recommended to seal with Precat Sealer or Duraseal high build sealer. May also be applied over suitable two component polyurethane sealers.

- **Coverage** Theoretical 15-20 square metres per litre
Practical 6-8 square metres per litre (Spray Application)

Uses: Used as an industrial grade quick drying NC pre-catalysed lacquer over suitably prepared timber surfaces. Intelac is ideal for use in industrial production lines for coating most internal furniture. Exhibits excellent film build with exceptional feel, ease of use, short recoat times and good durability.

APPLICATION

Timber must be of suitable grade for furniture manufacture with a moisture content not exceeding 12%. Timber must be prepared and sanded with at least 180 grit paper ready for application of coatings. Avoid applying coatings over oily timbers or knots containing sap, a suitable barrier coat may be necessary to avoid delamination or discolouration of topcoats.

SYSTEM 1/ SELF SEALING

Clear

1. Apply self sealer coat of Intelac and allow 2 hours cure @ room temperature.
2. Sand with 320 - 400 grit paper and recoat with Intelac at the desired gloss level.
3. If a third coat is needed allow two hours cure and repeat step 2.
4. If a third coat is needed allow two hours cure and repeat step 3.

Stained

1. Apply stain of desired colour and allow for recommended drying time.
2. Apply self sealing coat of Intelac and allow 2 hours cure @ room temperature.
3. Sand with 320 - 400 grit paper and recoat with Intelac at the desired gloss level.
4. If a third coat is needed allow two hours cure and repeat step 3.

SYSTEM 2/ SEALING

Clear

1. Apply 220PC Precat Sealer or Duraseal High Build sealer and allow 1-2 hours cure @ room temperature.
2. Sand with 320 - 400 grit paper and recoat with Intelac at the desired gloss level.
3. If a third coat is needed allow two hours cure and repeat step 2.

Stained

1. Apply stain of desired colour and allow for recommended drying time.
2. Apply 220PC Precat Sealer or Duraseal High Build sealer and allow 1-2 hours cure @ room temperature.
3. Sand with 320 - 400 grit paper and recoat with Intelac at the desired gloss level.
4. If a third coat is needed allow two hours cure and repeat step 3.

Note heavier coats will require longer recoat times

(Force curing of Intelac @ 40° C will allow a recoat time of approx 30 min)

Precautions:

Heavier coats will require longer recoat times. Care must be taken not to apply excessively high film builds of precatalysed lacquers of this type as this may lead to film defects and cracking.

(Force curing of Intelac @ 40° C will allow a recoat time of approximately 30 min)

Although Intelac is made from yellow resistant resins, nitrocellulose lacquers will yellow with age to some degree. Clear lacquer film will not prevent timber discolouration upon exposure to UV light. Intelac exhibits good splash resistance to water however, single component nitrocellulose lacquers are not recommended for use on vanity or kitchen bench-tops which may be exposed to water pooling or in areas exposed to high humidity, in such conditions two component chemical resistant coatings such as polyurethanes are recommended.

Single component Precat sealer may be replaced with a suitable two component Polyurethane sealer if higher film builds and improved resistance properties are required. Follow the recommended recoat times of the sealer used and sand between coats with 320 – 400 grit sand paper.

All advice, recommendations, information or service provided by Intec Coatings in relation to product manufactured or supplied by it or their use and application is given in good faith and is believed by Intec Coatings to be appropriate and reliable. This information may be subject to change without notice. No warranty expressed or implied is made as to its accuracy, completeness or otherwise provided that the foregoing shall not exclude, limit, restrict or modify the right entitlements and remedies conferred upon any person or the liabilities imposed upon Intec by any condition or warranty implied by Commonwealth, State or Territory Act or ordinance void or prohibiting such exclusion limitation or modification. Intec Coatings has no control on individual customer's application methods and or raw materials used and therefore can not be held responsible for product failure if recommended guidelines are not satisfied. Products are expected to perform as indicated provided the application procedures are adhered to.